



Class: S3 SRC Sizes: 35-47 Instep: 12

Weight(±10%): 469 gr. (*)

TECHNICAL SHEET ART. KAYAK

Description Low shoe in HIgh-Tex, 100% polyester lining, Non-Metallic HRP Insole, ESD Sport – Lite insole, double density polyurethane sole, bending resistant, abrasion resistant, oil resistant, slip resistant, ESD. Plus Midsole compound particularly studied to get a soft PU density for a higher comfort

Suggested sectors of usage Mechanical Industry, Building / Costruction , Logistic / Packaging , Professional / Craftsman , Servicing , Electronic & Electrotechnic.

Care and Maintenance clean periodically the outsole and the upper with non aggressive substances which could compromise quality, safety and durability of the shoe, do not dry close to direct heat source



Complete shoe	Norm	Description	Unit	FTG result	EN ISO 20345 requirement
Toe cap: THIN CAP toe cap , impact restistant 200 J	5.3.2.3	Impact resistance	mm	14,5	>= 14
	5.3.2.4	Compression resistance	mm	14,0	>= 14
Midsole: non metallic HRP Insole with high tenacity fibres layers, ceramized and treated with plasma	6.2.1.1	Perforation resistance	N	1.100	>= 1.100
ESD footwear: dissipation capacity of the electrostatic charge	EN ISO	Electric resistance			
	61340-5-1	Class 2	Mohm	30,0	< 35
Capacity of energy absorption in the heel area	6.2.4	Energy absorption in the heel area	J	25,0	>= 20
Upper: High- Tex , black color	5.4.6	Water vapour permeability	mg/cmq h	3,4	>= 0,8
		Coefficient of permeability	mg/cmq	30,7	>= 15
	5.4.3	Tearing strength	N	285	>= 60
Vamp lining: non woven textile for toe cap, grey color	5.5.3	Water vapour permeability	mg/cmq h	3,4	>= 2
		Coefficient of permeability	mg/cmq	30,2	>= 20
	5.5.1	Tearing strength	N	30	>= 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	25.600
		Abrasion resistance (wet)	cycles	no rupture	12.800
Quarter lining : 100% honeycomb finished polyester, breathable, abrasion	5.5.3	Water vapour permeability	mg/cmq h	6,8	>= 2
resistant , grey color		Coefficient of permeability	mg/cmq	54,4	>= 20
	5.5.1	Tearing strength	N .	25	>= 15
	5.5.2	Abrasion resistance (dry)	cycles	no rupture	51.200
		Abrasion resistance (wet)	cycles	no rupture	25.600
Insole lining: textile anti perforation midsole HRP insole	5.7.3	Water absorption	Mg/cm ²	78	>= 70
		Ability to release water	<i>5</i> ,	99%	>= 80%
Sole : Double density polyurethane, bending resistant, abrasion resistant, oil	5.8.2	Tearing strength	kN/m	10,5	>= 8
resistant , slip resistant , ESD	5.8.3	Abrasion resistance	mm ³	74	<= 150
	5.8.4	Bending resistance	mm	2,5	<= 4
	5.8.5	Hydrolysis	mm	1,0	<= 6
	6.4.2	Hydrocarbons resistance (volume increase)	%	0,3%	<= 12%
	5.11	Slip resistance on ceramic floor with water and	flat	0,42	>= 0,32
		detergent	inclined	0, 4 0	>= 0,28
		Slip resistance on steel floor with glycerine	flat	0,20	>= 0,18
		- ,	inclined	0,17	>= 0,13